

# SUPERTON 242 / 242 S / 242 W

## High Range Water Reducing Superplasticizing Concrete Admixture

### DESCRIPTION

SUPERTON 242 / 242 S / 242 W, is modified sulfonate based, highly water reducing, strength improving and superplasticizing concrete admixture.

### FIELD OF APPLICATION

- In all ready-mixed concrete classes described in TS EN 206 and TS EN 13515
- Low water/cement ratio concrete applications
- Impermeable concrete applications
- Smooth surface applications such as bridge/viaducts
- In construction of all building elements

### ADVANTAGES

- SUPERTON 242 / 242 S / 242 W,superplasticizer concrete admixture provides workability to fresh concrete without causing segregation
- Let the concrete mixing designs to be formed that have low water/cement rates
- Increases hardened concrete endurance against environmental effect conditions
- Does not include chloride ions. Does not cause paraphernalia corrosion
- It provides long term consistency protection to fresh concrete. This allows the fresh concrete mix to be transported over long distances.

### USE

- SUPERTON 242 / 242 S / 242 W is ready to use as liquid for fresh concrete mix. It is recommended that it is added to mixing water at ready-mixed concrete production station.

### USE OF WEATHER CONDITIONS

- |                            |                |
|----------------------------|----------------|
| • <b>The summer months</b> | SUPERTON 242 S |
| • <b>Winter months</b>     | SUPERTON 242 W |
| • <b>Transition months</b> | SUPERTON 242   |

### STANDARDS

- **SUPERTON 242 S** : TS EN 934-2 Table 11.1,11.2  
ASTM C 494 Tip G
- **SUPERTON 242 W** : TS EN 934-2 Table 3.1, 3.2  
ASTM C 494 Tip F
- **SUPERTON 242** : TS EN 934-2 Table 3.1, 3.2  
ASTM C 494 Tip F

### CONSUMPTION

It is recommended that the total binder existing in every type of concrete class mixing design described in TS EN 206 and TS EN 13515 standards is used between the rates of 0,5% and 2,0% by weight. This rate changes on concrete mixing design according to requested air quantity, cement features used, aggregate, mineral additive, water components, heat and also according to preferred fresh and hardened concrete features. Therefore, laboratory tests should be performed accordingly with preferred features and usage rate should be determined.

Since the air quantity to be entrained to concrete will increase additive dosage to be used, it is expected that concrete strength will fall.

### STORAGE CONDITIONS AND PACKAGING

The product must be stored above 5 °C. In case the product freezes it should be carefully mixed mechanically after thawing for restitution.

It is for sale as 25 kg plastic drum, 200 kg drums, 1000 kg plastic cubitainers and bulk.

### COMPATIBILITY

SUPERTON 242 / 242 S / 242 W, is compatible with Extraton, Airton, Antiton, Retarton, Proofton, Specialton Series POLISAN Construction Chemicals. For its compatibility information with other additives, one should consult Polisan Construction Chemicals technical support unit. If one is to use more than one additive substance on mixing design, each substance should be added to the mix separately.

It can be used with all cement types compatible with SUPERTON 242 / 242 S / 242 W, TS EN 197-1 standard and all mineral additives (fly ash, blast furnace slag, silica fume etc.) compatible with TS EN 206 and TS EN 13515 standards. For use on special types of cement, it is recommended to consult Polisan Construction Chemicals technical support unit.

### SAFETY INFORMATION

The additive must be kept away from the skin and eyes. In case of any contact, it must be washed with water. When contacted with eyes one must immediately rinse it with water and medical support must be taken. Protective goggles / gloves / mask should be used during the usage of the admixture.

The Material Safety Data Sheet (MSDS) should be read for detailed information